




<p>(51) International Patent Classification ⁵ : A61M 31/00, A61K 9/20, 9/22</p>	<p>A2</p>	<p>(11) International Publication Number: WO 90/15637 (43) International Publication Date: 27 December 1990 (27.12.90)</p>
<p>(21) International Application Number: PCT/US90/03492 (22) International Filing Date: 20 June 1990 (20.06.90) (30) Priority data: 369,296 21 June 1989 (21.06.89) US (71) Applicant: BROWN UNIVERSITY RESEARCH FOUNDATION [US/US]; 42 Charlesfield Street, Providence, RI 02912 (US). (72) Inventors: AEBISCHER, Patrick ; 97 University Avenue, Providence, RI 2960 (US). WINN, Shelley, R. ; 9 Hall Street, Providence, RI 02904 (US). (74) Agents: ENGELLENER, Thomas, J. et al.; Lahive & Cockfield, 60 State Street, Boston, MA 02109 (US).</p>		<p>(81) Designated States: AT (European patent), -AU, BE (European patent), CA, CH (European patent), DE (European patent)*, DK (European patent), ES (European patent), FI, FR (European patent), GB (European patent), IT (European patent), JP, KR, LU (European patent), NL (European patent), NO, SE (European patent). Published <i>Without international search report and to be republished upon receipt of that report.</i></p>
<p>(54) Title: NEUROLOGICAL THERAPY SYSTEM</p>		
<div style="display: flex; justify-content: space-around; align-items: flex-start;">    </div>		
<p>(57) Abstract</p> <p>Neurological therapy devices are disclosed for the local and controlled delivery of a neurotransmitter to the brain of a subject suffering from neurotransmitter deficiency or dysfunction. In one embodiment the device (100) includes a biocompatible, implantable, and retrievable polymeric insert (30) including a source of neurotransmitter embedded therein. In another embodiment, the device (200) includes a retrievable source of neurotransmitter including at least one neurotransmitter-secreting cell (52) encapsulated within a semipermeable membrane allowing the diffusion therethrough of the neurotransmitter, and further includes a source of growth factor in close proximity to the neurotransmitter-secreting cells.</p>		

DESIGNATIONS OF "DE"

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MC	Monaco
AU	Australia	FI	Finland	MG	Madagascar
BB	Barbados	FR	France	ML	Mali
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GR	Greece	NL	Netherlands
BJ	Benin	HU	Hungary	NO	Norway
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	SD	Sudan
CF	Central African Republic	KP	Democratic People's Republic of Korea	SE	Sweden
CG	Congo	KR	Republic of Korea	SN	Senegal
CH	Switzerland	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
DE	Germany, Federal Republic of	LU	Luxembourg	TC	Togo
DK	Denmark			US	United States of America

NEUROLOGICAL THERAPY SYSTEM

5

Background of the Invention

The technical field of this invention is the treatment of neurological diseases and, in particular, the treatment of neurotransmitter-deficiency and dysfunction diseases.

Neurotransmitters are small molecules (less than 1 kilodalton (kD) molecular weight) which act as chemical means of communication between neurons. They are synthesized by the presynaptic neuron and released into the synaptic space where they then effect receptors on postsynaptic neurons.

20 Neurotransmitter deficits have been implicated in various neurological diseases. Lack of neurotransmitter-mediated synaptic contact causes neuropathological symptoms, and can also lead to the ultimate destruction of the neurons involved. Recently, it has been discovered and disclosed in commonly-owned U.S. Patent Application Serial No. 121,626 that localized delivery of the relevant neurotransmitter to the target tissue may reverse the symptoms without the need for specific synaptic contact.

For example, paralysis agitans, more commonly known as Parkinson's disease, is characterized by a lack of the neurotransmitter, dopamine, within the striatum of the brain, secondary to the destruction of the dopamine secreting cells of the substantia nigra. Affected subjects demonstrate a stooped posture, stiffness and slowness of movement, and rhythmic tremor of limbs, with dementia being often encountered in very advanced stages of the disease.

These clinical symptoms can be improved by the systemic administration of dopamine precursors such as levodopa (L-dopa) (Calne et al. (1969) Lancet ii:973-976), or dopamine agonists such as bromocriptine (Calne et al. (1974) Bri. Med. J. 4:442-444) and (+)-4-propyl-9-hydroxynaphthoxacine (de Yebenes et al. (1987) Movement Disorders 2:291-299), both of which are able to cross the blood-brain barrier, and which are converted into dopamine in the brain. Dopamine, itself, cannot be administered systemically because of its inability to cross the blood-brain barrier.

25

However, a number of drawbacks are incurred when using this type of chemical therapy. For example, other neurological structures which recognize dopamine as a neurotransmitter are also affected. In addition, it becomes difficult to administer the correct drug dosage with time because the "therapeutic window" narrows (i.e., just after administration, the patient is overdosed, exhibiting

30

excessive spontaneous movement; some time thereafter the drug level may become insufficient, causing the patient to again express Parkinsonian symptoms). Furthermore, the limited potency and/or solubility of most available dopamine agonists precludes continuous in vivo infusions as means to reduce motor deficits in Parkinson's disease. Therefore, what is needed is a method of continuous or constitutive delivery of an undegraded, active neurotransmitter to a localized target region deficient in that neurotransmitter.

In an attempt to provide a continuous supply of dopamine and related drugs to the brain at a controlled rate, miniature osmotic pumps have been used. However, limited solubility and stability of dopamine and related drugs, as well as reservoir limitations, have restricted the usefulness of this technology. Controlled sustained release has also been attempted by implanting dopamine encapsulated within bioresorbable microcapsules (McRae-Degueurce et al. (1988) Neurosci. Lett. 92:303-309). However, controlled sustained release of a drug from a bioresorbable polymer relies on bulk surface erosion, for example, due to various hydrolytic events, increasing the likelihood of drug degradation, and rendering predictable release rates difficult.

The implantation of cells capable of constitutively producing the needed neurotransmitter, reportedly in response to environmental needs, has also been attempted. Recently, remedial transplantation of neurotransmitter-secreting tissue has been accomplished using the patient's own tissue so

as not to elicit an immune response. For example, dopamine-secreting tissue from the adrenal medulla of patients suffering from Parkinson's disease has been implanted in their striatum with some success.

5 However, this procedure is only used in patients less than 60 years of age, as the adrenal gland of older patients may not contain sufficient dopamine-secreting cells. This restriction limits the usefulness of the procedure as a remedy since the

10 disease most often affects older people.

Furthermore, abdominal surgery performed to excise portions of the adrenal gland poses substantial risks. Moreover, it is not actually

15 known whether it is the dopamine or other "factors" produced by the implanted cells, or the trauma of the surgery, itself, which alleviates the clinical symptoms. In fact, stereotaxic surgery, or the placement of precisely localized lesions in the brain

20 has been practiced in younger, less affected patients without transplantation and this procedure appears to provide similar relief of Parkinsonian symptoms. The procedure is risky, however, and opinions among neurosurgeons still differ as to the best way of

25 making the lesion and what its ideal location should be.

Alternatives to the transplantation of a patient's brain tissue also include the

30 transplantation of either allograft (identical tissue from another of the same species), or xenograft (similar tissue from another of a different species) dopamine-secreting tissue. However, recent studies

have shown that although the brain is considered "immuno-privileged", rejection ultimately occurs with both allografts and xenografts. This problem
5 necessitates the co-administration of immuno-suppressors, the use of which renders their own set of complications and deleterious side-effects.

Therefore, there exists a need for improved
10 therapies for neurotransmitter-deficiency diseases in general, and in particular, a need for neurological therapy devices which can augment or replace the functions of dysfunctional neurotransmitter-producing areas of the brain without causing excessive trauma.
15 More specifically, there exists a need for a method of providing active, undegraded neurotransmitter to a localized region of the nervous system of a subject deficient in this neurotransmitter, the correct dosage of which will be constitutively delivered over
20 time.

Accordingly, it is an object of the present invention to provide an implantable neurological therapy device useful for the sustained and
25 controlled delivery of a neurotransmitter to a subject, and more particularly, to provide a device which can deliver neurotransmitter to a localized region in the brain of a subject.

It is another object to provide an implantable device that contains and protects neurotransmitter therein from in vivo degradation
5 such that it is delivered to the subject in an active form. Yet another object of the present invention is to provide an implantable device which can deliver an amount of neurotransmitter responsive to in vivo environmental needs. A further object is to provide
10 an implantable, protective cell culture device which is retrievable, and whose contents are renewable with new and/or additional source of neurotransmitter.

Summary of the Invention

Neurological therapy devices are disclosed
5 for the local and controlled delivery of a
neurotransmitter to the brain of a subject suffering
from a neurotransmitter deficiency or dysfunction.
It has been discovered that various polymeric
materials have the ability to protect various
10 "effector-type" substances, such as neurotransmitters
and growth factors, from oxidation, hydrolysis, and
degradation when such substances are embedded
therein. In addition, these polymeric materials have
the capacity for sustained release of the embedded
15 substance at a controlled rate. Recently, it has
also been discovered that cells encapsulated within a
protective semipermeable membrane, and not in direct
contact with a target tissue, are capable of
producing neurotransmitter or growth factor in
20 response to the needs of the immediate environment.

These discoveries have been utilized to
develop the neurological therapy devices of the
present invention. One such device includes a
25 biocompatible, implantable, and retrievable polymeric
insert including a source of neurotransmitter. In
preferred embodiments of this device, the source
includes a neurotransmitter which has been embedded
within the insert. The polymeric insert protects the
30 neurotransmitter embedded therein from oxidation,
enzymatic degradation, and hydrolysis. It may take

any shape which is conducive for supplying neurotransmitter, and which can be accommodated by the recipient. Preferred shapes include a fiber or rod.

5

Useful neurotransmitters to be embedded within the insert include gamma aminobutyric acid, serotonin, acetylcholine, norepinephrine, endorphins, enkephalins, and dopamine. Alternatively, precursors, agonists, active analogs, and active fragments of these neurotransmitters (e.g. dopamine precursor L-dopa and dopamine agonist bromocriptine) may be used.

15

The polymeric insert includes pores having a molecular weight exclusion of from about 1 kD to about 1,000 kD, but preferably from about 25 kD to about 100 kD. In one preferred embodiment, the polymeric insert includes a hydrophobic matrix such as ethylene-vinyl acetate copolymer. In another embodiment, the insert includes a hydrophilic matrix such as a hydrogel. The insert may additionally include an impermeable portion which is preferably provided by an outer coating of a pure polymeric material such as polyurethane or ethylene-vinyl acetate. The impermeable portion can serve to make the insert function as a conduit for neurotransmitter or whatever substance is embedded therein, and can also aid in supplying the substance to a specific anatomical region of the subject.

20
25
30

An alternative neurological device includes a retrievable source of neurotransmitter and a retrievable source of growth factor in close proximity. The source of neurotransmitter includes at least one neurotransmitter-secreting cell encapsulated within a semipermeable membrane allowing the diffusion therethrough of the neurotransmitter.

10 The term "semipermeable" is used herein to describe biocompatible membranes that allow the diffusion therethrough of molecules having a relatively low molecular weight, while excluding the passage of those having a relatively high molecular weight.

In one embodiment of the invention, the semipermeable membrane of the receptacle contains pores having a molecular weight exclusion of from about 50 kD to about 100 kD. This membrane excludes the passage therethrough of large particles such as those which are capable of degrading the neurotransmitter or injuring the neurotransmitter-producing cells (e.g. viruses, antibodies, complement, and various proteases). The semipermeable membrane can be made of various polymeric compositions such as a polyvinylchloride, polyacrylonitrile, polyvinylidene fluoride, polystyrene, polymethylmethacrylate, polysulfone, and acrylic copolymers.

The neurotransmitter-secreting cell may include any cell which is known, or has been engineered to produce neurotransmitter, or agonists, precursors, active analogs, or active fragments thereof. For example, chromaffin cells of the adrenal medulla, embryonic ventral mesencephalic tissue, and various neuroblastic cell lines such as PC12 function to supply dopamine, and therefore, are preferred for incorporation into the device. In some aspects of the invention, the cell is an allograft (i.e., cells from another of the same species as the subject in which it is to be implanted) or a xenograft (i.e., cells from another of a different species).

The source of growth factor is situated such that it can easily come into contact with the neurotransmitter-secreting cells encapsulated within the semipermeable membrane. The growth factor maintains cell differentiation and/or stimulates the production and secretion of neurotransmitter. In one preferred embodiment, the source of growth factor includes a polymeric insert with growth factor embedded therein. In another preferred embodiment, the source is at least one growth factor-secreting cell encapsulated within a semipermeable membrane allowing the diffusion therethrough of the growth factor. The growth factor is delivered to the neurotransmitter-secreting cells as it leaches from the insert or as it diffuses from the semipermeable membrane after being secreted by the cells therein.

The invention will next be described in connection with certain illustrated embodiments. However, it should be clear that various
5 modifications, additions, and subtractions can be made without departing from the spirit or scope of the invention. For example, the present invention should not be read to require, or be limited to, a particular device shape, material, neurotransmitter,
10 growth factor, or cell line described by way of example or illustration.

Brief Description of the Drawings

The invention itself can be more fully understood from the following description when read together with the accompanying drawings in which:

FIGS. 1A-1C are schematic illustrations of an implantable neurological therapy device according to several aspects of the present invention;

10

FIG. 2 is a graphic representation of cumulative in vitro release kinetics of eight dopamine/ethylene-vinyl acetate inserts;

15

FIG. 3 is a graph demonstrating rotational behavior of animals after the implantation of dopamine-containing neurological therapy devices;

FIG. 4 is a graph showing extracellular dopamine levels in the brain of animals having acutely implanted dopamine-containing neurological therapy devices;

FIG. 5 is a graph showing the level of extracellular dopamine in the brain of 3 animals having an implanted dopamine-containing neurological therapy device 7 days post-implantation; and

FIG. 6 is a photographic representation of a scanning electron micrograph of a dopamine/copolymer EVAc insert revealing dopamine particles distributed throughout the polymer matrix (A) before implantation, and (B) after implantation.

Detailed Description of the Invention

Neurological therapy devices are disclosed for the constitutive and controlled delivery of a neurotransmitter, a precursor, agonist, active fragment, or active analog thereof to a target region of a subject suffering from a neurological dysfunction.

10 Exemplary embodiments of the neurological therapy device of the present invention are shown in FIGS. 1A-1C in which like reference characters indicate the same or essentially similar elements in the various illustrations. FIG. 1A is a device
15 including an implantable, biocompatible polymeric insert containing the neurotransmitter embedded therein. The device 100 includes a cylindrical cap 20 having grooves 22 on the sides thereof, and a polymeric insert 30 containing neurotransmitter
20 embedded therein. The insert has a permeable portion 32, an impermeable portion 34, and an end 36. Neurotransmitter can diffuse through permeable portion 32, but not through impermeable portion 34.

25 The insert of the neurotherapy device acts as a conduit for the source of neurotransmitter or growth factor as well as a directed passageway to the anatomical region or specific tissue which requires treatment. In FIG. 1A the insert has the shape of a
30 rod. However, it should be appreciated that the insert may have any shape which can accommodate the source of neurotransmitter without causing undue trauma in the subject upon its surgical implantation.

The neurological therapy devices shown in FIGs. 1B and 1C include a source of neurotransmitter and a source of growth factor in close proximity. The device 200 shown in FIG. 1B includes insert 30 which contains growth factor embedded therein, and further includes semipermeable membrane 50 containing neurotransmitter-secreting cells 52 encapsulated therein. Membrane 50 has the form of a U-shaped tube. However, it should be appreciated that the semipermeable membrane may have alternative shapes that will accommodate the cells such as, for example, a hollow rod, sack, or multiple fibers.

U-tube 50 may be loaded with cells through end 26 or 28. Ends 26 and 28 may be reversibly occluded with friction fitted caps 40, or alternatively with an epoxy glue or sutures of a biocompatible and nonresorbable material. In the device 300 shown in FIG. 1C, semipermeable membrane 50 containing neurotransmitter-secreting cells 52 is accompanied by rod-shaped semipermeable membrane 54 containing growth factor-secreting cells 56 encapsulated therein.

The region targeted for implantation of the neurological therapy device is preferably the brain, as it is often the site of many neurological deficiencies and dysfunctions. Devices 100, 200, and 300 can be surgically implanted into the brain such that permeable portion 32 of insert 30, or semipermeable membrane 50 and 54 are in immediate contact with brain tissues and fluids. Once implanted, the cylindrical cap 20 can be permanently

secured to the skull, for example, by screwing it in, and further, by applying a glue or a cement such as dental cement to the cap at the junction of the skull and the cap.

5

In the event that the neurotransmitter or growth factor supply in insert 30 is spent, the insert can be removed and replaced. Retrieval of implanted insert 30 can be accomplished by pulling it
10 out of cap 20, for example, using a pair of forceps after exposing the device. Cap 20 may be located directly under the patient's epithelial tissues. Insert 30 may be replaced with a new insert in the event that additional neurotransmitter therapy is
15 required. Cells encapsulated within semipermeable membrane 54 (FIG. 1C) can also be retrieved if the cells cease to produce neurotransmitter or growth factor, expire, or are no longer needed to correct the neurological dysfunction. Cells in membrane 50
20 can be replenished by forcing the cells out of end 26 or 28 by pressure or suction using, for example, a hypodermic syringe.

Permeable portion 32 of insert 30 is
25 implanted at or near the target region, while the impermeable portion 34 confines the neurotransmitter or growth factor to within the boundaries of the insert. The permeable portion 32 includes a polymeric material having pores of a particular size
30 (i.e., having a particular molecular weight cut-off) that excludes some molecules from passage therethrough, while permitting the passage of others. In this way, the diffusion of

neurotransmitter from the insert to the target region, or growth factor to the neurotransmitter-producing cells, is allowed, while the passage of larger deleterious elements such as viruses, antibodies, complement, and various proteases is effectively barred. For example, inserts with pores having a molecular weight exclusion of from about 1 kD to about 1000 kD are useful, with those having pores with a molecular weight cut off of from about 25 kD to about 100 kD being particularly preferred.

The insert may be composed of any biocompatible material having the desired pore size and being composed of materials which do not limit the activity of the substance embedded therein. Hydrophilic matrices such as hydrogels (e.g., hydroxyethyl methacrylate, polyvinyl alcohol, and polyvinyl pyrrolidone) and hydrophobic matrices such as ethylene vinyl acetate are particularly useful.

20

The neurological therapy device can provide any neurotransmitter which will satisfy the deficiency or remedy the dysfunction. These include gamma aminobutyric acid, serotonin, acetylcholine, epinephrine, norepinephrine, dopamine, enkephalins, and endorphins. Alternatively, the device may provide an active analog, active fragment, or active derivative of the neurotransmitter, or may include a precursor, which after processing, provides the same activity as the neurotransmitter in the appropriate in vivo location. The device may further include an agonist of the neurotransmitter.

One way of providing the source of neurotransmitter includes incorporating it into the polymeric insert. The encapsulating material
5 provides a protective environment for substances such as neurotransmitters or cell growth factors embedded therein, while affording sustained release of the substance at a controlled rate therefrom. For instance, the use of polymeric insert composed of
10 hydrophobic matrices reduces neurotransmitter degradation by inhibiting oxidation and hydrolysis of the neurotransmitter encapsulated therein.

An exemplary method for incorporating the
15 effector substance (e.g., neurotransmitter or growth factor) into the insert includes fabricating the polymeric from a mixture or complex of the polymeric material and the substance. For example, a hydrophobic material such as ethylene-vinyl acetate
20 (EVAc) copolymer can be dissolved in a solvent to which a lyophilate of a neurotransmitter such as dopamine can be added. The mixture is agitated and fabricated into the desired shape by extruding it from a melt. Upon cooling of the mixture, a solid
25 polymeric matrix containing neurotransmitter embedded throughout the matrix is formed (see FIG. 6). Contact of the hydrophilic neurotransmitter with the aqueous environment causes the slow leaching of neurotransmitter therefrom, leading to the
30 development of micropores throughout the matrix of the insert.

The concentration of neurotransmitter added to the hydrophobic matrix material is one factor controlling the rate of neurotransmitter release; the more neurotransmitter incorporated, the more rapid the release rate. The particulate size of the neurotransmitter incorporated into the matrix material is another variable; the larger the particle size, the quicker the rate of release.

10

The release of growth factor from a polymeric insert can be controlled by the amount of carrier protein co-embedded therewith; the more carrier protein incorporated, the higher the rate of growth factor release. However, the ratio of growth factor to carrier protein is dependent on the levels of growth factor that are effective in the physiologic environment within a therapeutic range. A useful carrier protein is one having the ability to readily dissolve while in the matrix, and having the ability to leach from the matrix. Micropores through which growth factor can leach are created in the matrix when the carrier protein is dissolved by the aqueous environment. Such a carrier protein is bovine serum albumin (apparent molecular weight = about 69 kD).

The release rate may also be controlled by the amount of pure, impermeable polymeric material coating the effector substance-embedded insert; the more (or thicker the) coatings, the slower the release rate. Materials such as polyurethane or pure ethylene-vinyl acetate are particularly useful for this purpose.

Alternative methods of incorporating the source of neurotransmitter include the provision of neurotransmitter-producing cells accompanied by a
5 source of growth factor situated in close proximity thereto. In this embodiment, a semipermeable membrane functions as a protective cell culture device for the neurotransmitter-secreting cells. The pores of the membrane should be large enough to
10 enable the exchange of metabolites with body fluids, and to permit the diffusion therethrough of neurotransmitter produced by the cells therein, but are small enough to bar the passage therethrough of larger elements deleterious to the cells. Pores
15 having a molecular weight cut-off of from about 50 kD to 100 kD are particularly useful for this purpose.

The semipermeable membrane may take any useful form such as a U-tube, hollow fiber, cell sack
20 or container, or microcapsule. Likewise, if the source of growth factor includes growth factor-producing cells, they, too are encapsulated within a membrane allowing for the exchange of metabolites, growth factor production and diffusion, cell
25 maintenance, and growth (limited by the boundary of the membrane). For a further discussion of such devices, see commonly-owned, copending U.S. Application Serial No. 121,626, filed November 17, 1987, the disclosure of which is hereby incorporated
30 by reference.

Any cells which secrete the desired neurotransmitter or growth factor may be incorporated into the device. For example, the cells may be any
5 which naturally produce the neurotransmitter, such as neurons. Such cells are useful because they are able to respond to the general environment by producing neurotransmitter as it is needed. The cells can be obtained from a number of sources such as a body
10 organ which normally secretes a particular neurotransmitter in vivo. For example, tissues of the embryonic ventral mesencephalon and adrenal medulla (chromaffin cells) which normally produce dopamine can be used. These tissues may be an
15 allograft, or they may be a xenograft. Alternatively, the cell may be derived from various cultured neuroblastoid cell lines, such as PC12.

In addition, any cell which secretes a
20 precursor, agonist, active analog, or active fragment of a desired neurotransmitter or growth factor having similar neurotransmitter activity can also be used, including, for example, cells which elicit L-dopa, a precursor of dopamine, or bromocriptine, a dopamine
25 agonist.

Further, any cells which have been genetically engineered to express a neurotransmitter or growth factor, or their agonists, precursors,
30 derivatives, analogs, or fragments thereof having similar effector activities are also useful in practicing this invention. Thus, in such an approach, the gene which encodes the

neurotransmitter, or its analog or precursor is either isolated from a cell line or constructed by DNA manipulation. The gene can then be incorporated into a plasmid, which, in turn, is transfected into a cell such as a fibroblast for expression. (See, e.g., Maniatis et al., Molecular Cloning (1982), herein incorporated by reference for further discussion of cloning vehicles and gene manipulation procedures.) The cells which expresses the neurotransmitter can be grown in vitro until a suitable density is achieved.

Thereafter, the cells from this culture can be loaded into the neurological therapy device by seeding a portion of the already implanted semipermeable membrane via an orifice located at the skin surface. Alternatively, small tissue fragments or culture aggregates may be preloaded into an encapsulating semipermeable membrane which is then implanted within the subject.

Various "growth factors" having the ability to stimulate cell growth, differentiation, and/or neurotransmitter secretion may be co-implanted with the neurotransmitter-secreting cells to insure successful delivery of neurotransmitter to the subject. These growth factors may be specific for a cell type or have a generalized effect on a number of different tissues. In the case of neurotransmitter-producing cells such as neurons, growth factors can act to maintain neurotransmitter production, as well as to promote cell maintenance and growth. Alternatively, growth factors may maintain nerve

cells in a differentiated state. Useful cell growth factors include nerve growth factor (NGF), fibroblast growth factor (FGF), platelet-derived growth factor (PDGF), and epidermal growth factor (EGF), among
5 many. In addition, effectors of various membrane receptors such as glutamate and nicotine may also be useful.

The growth factor may be incorporated into
10 the device with the neurotransmitter-producing cells by embedding it within the polymeric matrix of the insert and placing it in the receptacle with the cells. The embedded growth factor leaches slowly from the insert into the receptacle, thereby acting,
15 for example, to maintain the differentiated state of the cells therein such that they continue to produce neurotransmitter. The encapsulating membrane of the cells, if present, poses no hindrance as it is permeable to the growth factor. This insert may be
20 retrieved from the receptacle and replaced as described above.

Alternatively, growth factor-producing cells such as hippocampal cells or fibroblasts engineered
25 to produce NGF (see e.g., Rosenberg et al. (1988) Science 242:1575-1578) may be encapsulated and implanted in proximity to the neurotransmitter-secreting cells as described above.

30 The following non-limiting examples more fully illustrate preferred features of the invention.

EXAMPLE I

Experimental Model

5 Young adult (200-225 g) male Sprague-Dawley
rats (Charles River Laboratory, Wilmington, MA) were
anesthetized by intramuscular injection of an 87/13
mg/kg mixture of ketamine (Ketalar*)/ xylazine
(Rompun*). Stereotaxic injections of 6-OHDA
10 (12 mg 6-OHDA in 6 µl of 0.9% saline with 0.05 mg/ml
of ascorbic acid) were performed into the
anteriomedial region of the substantia nigra
(coordinates: -2.9 mm bregma, 2.3 mm lateral and 8.1
mm deep to the dura with the incisor bar set at 5.0
15 above the intraaural line). Two weeks after the
lesion, rotational behavior was assessed under
apomorphine (APO) (0.05 mg/kg sc) challenge.
Behavior was characterized both in an open field and
modified Ungerstedt rotometer essentially as
20 described by Ungerstedt et al. (Brain Res. (1970)
24:485-493). Animals exhibiting more than eight
turns/minute over a 40 minute test period were
selected for the study. Groups of 3 animals were
housed in plastic cages on a 12 hour on-off light
25 cycle, with food and water available ad libitum.

EXAMPLE 2

Intracranial Cannulation

30 Sixteen animals received intrastriatal
devices made of a 9.5 mm long (0.85 mm ID)
semipermeable polyvinylchloride-acrylic copolymer
(AC) tubular inserts with a molecular weight
exclusion of 50 kD. The distal end of the insert was

occluded with a solution of the same acrylic copolymer. The first 6 mm from the open end of the insert were coated with a polyurethane solution, rendering this portion impermeable, and therefore, limiting fluid exchange to the striatum.

Sterilized therapy devices were inserted stereotaxically into the striatum (+0.3 mm bregma, 2.7 mm lateral to the midline and 8.0 mm deep to the dura). Once implanted, the therapy devices were secured by equidistant placement of 2 bone screws into the skull, providing anchorage for dental cement. The proximal port was closed with an AC glue. The therapy device remained in vivo for the duration of the study.

The implantation of empty striatal therapy devices did not induce any new neurological deficits in any of the animals. At the time of implantation of the acrylic copolymer inserts, the proximal cap of the therapy device was hermetically fused to the tube. After cap removal, the device lumen was filled with an acellular clear liquid.

25

EXAMPLE 3

Dopamine-Releasing Insert Fabrication

Ethylene-vinyl acetate copolymer (EVAc) resin (40% by weight vinyl acetate, Elvax 40w, DuPont, Inc., Wilmington, DE) was washed 20 times in distilled water and 95% ethanol to remove impurities. Purified EVAc was subsequently dissolved in methylene chloride to make a 10% (w/v) solution. Dopamine (Sigma, St. Louis, MO) was ground in a

mortar to a fine powder, sieved to 50 μ m, and added to the EVAc solution to a final concentration of 20% dopamine to EVAc (w/w). The dopamine/EVAc solution was ultrasonicated for 5 minutes, agitated in a 5 vortex mixer for 15 minutes, and rapidly cooled in liquid nitrogen in order to form a solid matrix with fixed dopamine particles. The methylene chloride was removed by lyophilization.

10 Strings with a diameter of 0.5 mm were pressure extruded at a temperature of 55°C and sectioned into rods 8 mm long. To retard dopamine release, three coats of 10% EVAc were applied to each rod by repeated immersion resulting in rods with a 15 final diameter of 0.7 mm. The distribution of dopamine particles in the EVAc was analyzed by scanning electron microscopy (AMRay-1000A, Lico, Inc., Bedford, MA).

20

EXAMPLE 4

In Vitro Release Kinetics

In vitro dopamine release kinetics were studied by placing a 0.7 x 8 mm long rod in 1 ml of 25 0.9% physiologic saline with 0.05 mg/ml of ascorbic acid (+) or (-) 20% dopamine incubated in individual wells at 37°C. At daily time-points, the fluid was collected and its concentration measured by high pressure liquid chromatography (HPLC) with an 30 electrochemical detector. The system used included a Model 5700 solvent delivery module and a model 5100A Coulochem multi-electrode electrochemical detector (ESA, Bedford, MA). A 20 μ l aliquot of each sample was injected onto the column (CA-HR 80; ESA) with no

sample pretreatment. The mobile phase contained 0.05 M NaPO₄, 0.2 M EDTA, 212 mg/L heptane sulfonic acid, and 3% methanol, at a pH of 2.6. Total run time was approximately 8 min. The concentration of each
5 compound was determined by comparison with the peak height of serial diluted standards run with each assay. The dopamine detection limit of the chromatographic system used was 50 pg.

10 The wells were replenished with fresh saline/ascorbate solution after each measurement. Dopamine release was calculated as cumulative percent release.

15 FIG. 2 shows the cumulative dopamine release of eight 0.7 x 8 mm 20% dopamine/EVAc rods in 0.9% physiologic saline with 0.05 mg/ml ascorbic acid at 37°C over 17 days (FIG. 2). Total dopamine content prior to the release studies amounted to 340 +/- 25
20 mg per rod.

EXAMPLE 5

In Vivo Studies

25 Successfully lesioned animals with striatal therapy devices were anesthetized and placed in a stereotaxic apparatus. Following midline incision, the proximal cap on the therapy device was located and excised, and a 20% dopamine/EVAc insert rod was
30 placed in the cap of the device. The proximal end of the device was again sealed with the AC glue. Skin closure was achieved with 6-0 monofilament nylon (Ethicon, Inc., Somerville, NJ).

Rotation behavior was evaluated under apomorphine challenge (0.05 mg/kg) at 7 and 14 days post-dopamine/EVAc loading. The dopamine/EVAc rod 5 was subsequently removed from the receptacle under methoxyfluorane anesthesia at day 14. Behavior was analyzed two and four weeks later.

During the first few hours after
10 implantation, the animals receiving dopamine/EVAc inserts spontaneously rotated contralateral to the implant side, whereas animals receiving control inserts did not exhibit such behavior. FIG. 3 summarizes the effect of the APO challenge before,
15 during, and after the implantation of a 20% dopamine/EVAc inserts as compared to control animals, who had received inserts of EVAc alone. Controls showed a slight improvement in rotational behavior 7 days post-implantation with return to pre-
20 implantation values at all subsequent time points. Experimental animals displayed a statistically significant decrease in rotational behavior at both 7 and 14 days post-implantation (30.1% at 7 days and 82.6% at 14 days). Two weeks after the removal of
25 the dopamine-release insert, rotational behavior increased again, leaving no statistical difference between the control and the experimental group at 42 days.

EXAMPLE 6

Dopamine Determination

The microdialysis probes used in these experiments were composed of AC semipermeable tubes (600 μ m ID, 8 mm long, 50 kD molecular weight exclusion) fabricated by a phase-inversion, dry-jet wet spinning technique (de Yebenes et al. (1987) Movement Disorders 2:291-299). A few hours prior to the experiment, the dialysis probe recovery was determined by placing the probe in a beaker of artificial cerebrospinal fluid (CSF) (150 mmol Na⁺, 1.4 mmol Ca⁺⁺, 0.8 mmol Mg⁺⁺, 1.0 mmol PO₄, 155 mmol Cl⁻, pH 7.4) containing known concentrations of dopamine, DOPAC, and DHBA at 800 pg/20 ml with 1 mg ascorbic acid in a 100 ml solution. Dopamine concentration was determined by HPLC with an electrochemical detector (EC). The system used included a Model 5700 solvent delivery module (ESA, Bedford, MA) and a model 5100A Coulochem multi-electrode electro-chemical detector (ESA, Bedford, MA). The relative recovery of the dialysate probes was 24-29% at room temperature. Dialysate values are reported as pg per 20 minute collection period.

For in vivo analyses, a dialysis probe was stereotaxically placed in proximity to the previously implanted receptacle in the rat striatum. The animal was anesthetized as previously described. Artificial CSF was pumped through the probe at a flow rate of 2.5 ml/minute throughout the experiment. The dialysate was collected over 20 minute intervals into

tubes containing 5 ml 1.1 N perchloric acid. The sample was analyzed immediately by HPLC-EC.

After collecting a number of samples to
5 determine baseline extracellular fluid (ECF) dopamine
overflow, a 20% dopamine/EVAc insert was placed in
the therapy device. Dialysis samples were collected
for 20 minute intervals post-implantation to
determine if ECF dopamine levels were affected by the
10 dopamine-releasing insert. Dopamine levels were
determined acutely following the implantation of the
dopamine-EVAc inserts in 3 animals and 7 days post-
implantation in the 3 remaining animals.

15 A 20 ml aliquot of each sample was injected
onto the column (CA-HR 80, ESA) with no sample
pretreatment. The mobile phase contained 0.05 M
NaPO₄, 0.2 M EDTA, 212 mg/L heptane sulfonic acid,
and 3% methanol, at pH 2.6. Total run time with
20 resolution of dopamine and DOPAC was approximately 11
minutes. The concentration of each compound was
determined by comparison with the peak height of
serial diluted standards run with each assay.

25 As shown in FIG. 4, dopamine levels in the
extracellular fluid of lesioned striata were
consistently undetectable by microdialysis. Twenty
minutes after the implantation of a 20% dopamine-
releasing EVAc polymeric insert, high levels of
30 dopamine were recovered. The dopamine levels
remained elevated throughout the next 80 minutes. In
a lesioned striatum studied seven days post-
implantation of dopamine/EVAc, the extracellular

striatal dopamine concentration in the dialysate was comparable to the levels observed in the acute experiment shown in FIG. 5. Histologically, the microdialysis probes were found to be located 300-500 μ m from the devices.

EXAMPLE 7

Histology

10 Upon completion of the study, deeply anesthetized animals were perfused transcardially. The brain was removed and sections 25 μ m thick were cut on a freezing sliding microtome (AO Reichert Model 976 C, Austria), and either picked-up directly
15 on glass slides coated with 3-amino-propyltriethoxysilane, or immersed directly in Tris buffer. Selected sections were stained for Nissl substance with cresyl violet. Such histological analysis revealed consistent placement of the receptacle
20 within the striatum.

Other sections were processed for immunocytochemical localization of tyrosine hydroxylase (TH) utilizing the avidin-biotin
25 procedure. Brain sections were incubated 2 days at 4°C in primary antisera to TH (Eugene Tech, Allendale, NJ). Incubations in the secondary antisera and the Avidin-Biotin complex (Vectors Labs, Burlingame, CA) were carried out at room temperature
30 and the peroxidase reaction was developed essentially as described by Winn et al. (J. Biomed. Mater. Res. (1989) 23:31-44). Mounted slides were analyzed with a Zeiss IM 35 interfaced with a morphometric system (CUE-2, Olympus Corp., Lake Success, NY).

At the conclusion of the study, immunohistochemical localization of TH on the substantia nigra and the striatum confirmed greater than 90% destruction of the nigrostriatal pathway. No evidence of sprouting surrounding the device was observed.

The 20% dopamine/EVAc insert were examined by scanning electron microscopy (SEM) using an AMRay 1000A machine (Lico, Inc., Bedford, MA) prior to and 2 weeks after implantation (FIG. 6). Cross-sectional scanning electron microscopy revealed an even distribution of dopamine particles suspended throughout the polymer matrix (FIG. 6A). Two weeks after incubation in physiologic saline and *in vivo*, the polymer inserts showed disseminated pits and holes, indicative of dopamine particle dissolution (FIG. 6B).

20

EXAMPLE 8

Implantation of Dopamine-Producing Cells and Nerve Growth Factor-Releasing Inserts

EVAc inserts containing 0.01 - 0.2% nerve growth factor (NGF) were prepared as described in EXAMPLE 3 except that dopamine is replaced with NGF. NGF/EVAc inserts were implanted within the striatal neurotherapy devices of successfully lesioned animals as described in EXAMPLE 5. A suspension of adrenal medulla chromaffin cells was prepared by enzymatic dissociation. The suspension was seeded within the semipermeable membrane by injection of cells in suspension. The proximal end of the device was

30

sealed with AC glue, and skin closure was achieved with 6-0 monofilament nylon (Ethicon, Inc., Somerville, NJ). Rotational behavior was evaluated as described in EXAMPLE 5 at 7, 14, 21, and 28 days 5 post-NGF/EVAc and cell loading.

Behavioral modification tests and histological analysis after implantation were performed as described in EXAMPLES 5-7, revealing 10 essentially similar results.

What is claimed is:

1. A neurological therapy device for the local and controlled delivery of a neurotransmitter to the brain of a subject, said device comprising a
5 biocompatible, implantable, and retrievable polymeric insert including a source of a neurotransmitter for controlled release of said neurotransmitter.

2. The device of claim 1 wherein said
10 neurotransmitter is selected from the group consisting of gamma aminobutyric acid, serotonin, acetylcholine, norepinephrine, endorphins, enkephalins, dopamine, and precursors, agonists, active analogs, and active fragments thereof.

15

3. The device of claim 2 wherein said neurotransmitter is a dopamine precursor comprising L-dopa.

20 4. The device of claim 2 wherein said neurotransmitter is a dopamine agonist comprising bromocriptine.

5. The device of claim 1 wherein said polymeric
25 insert includes pores having a molecular weight exclusion range from about 1 kD to about 1,000 kD.

6. The device of claim 5 wherein said polymeric
insert contains pores having a molecular weight
30 exclusion range from about 25 kD to about 100 kD.

7. The device of claim 1 wherein said polymeric insert comprises a hydrophobic matrix.

8. The device of claim 7 wherein said hydrophobic matrix comprises an ethylene-vinyl acetate copolymer.

5 9. The device of claim 1 wherein said polymeric insert comprises a hydrophilic matrix.

10 10. The device of claim 9 wherein said hydrophilic matrix comprises a hydrogel.

11. The device of claim 1 wherein said polymeric insert further comprises an impermeable outer coating covering a portion of said insert.

15 12. The device of claim 11 wherein said impermeable outer coating comprises polyurethane.

20 13. The device of claim 11 wherein said impermeable outer coating comprises ethylene-vinyl acetate.

14. A neurological therapy device for the local and controlled delivery of a neurotransmitter to the brain of a subject, said device comprising:

25 a retrievable source of neurotransmitter including at least one neurotransmitter-secreting cell encapsulated within a semipermeable membrane, said semipermeable membrane allowing the diffusion therethrough of said
30 neurotransmitter; and
a retrievable source of a growth factor located in close proximity to said neurotransmitter source.

15. The device of claim 14 wherein said neurotransmitter is selected from the group consisting of gamma aminobutyric acid, serotonin,
5 acetylcholine, norepinephrine, endorphins, enkephalins, dopamine, and precursors, agonists, active analogs, and active fragments thereof.

16. The device of claim 15 wherein said
10 neurotransmitter is a dopamine precursor comprising L-dopa.

17. The device of claim 15 wherein said neurotransmitter is a dopamine agonist comprising
15 bromocriptine.

18. The therapy device of claim 14 wherein said semipermeable membrane within which said neurotransmitter-secreting cell is encapsulated is
20 impermeable to viruses, antibodies, complement, and proteases.

19. The device of claim 14 wherein said semipermeable membrane includes pores having a
25 molecular weight exclusion of from about 50 kD to about 100 kD.

20. The device of claim 14 wherein said semipermeable membrane comprises an acrylic copolymer.
30

21. The device of claim 14 wherein said neurotransmitter-secreting cell comprises an allograft.

22. The device of claim 14 wherein said neurotransmitter-secreting cell comprises a xenograft.
23. The device of claim 14 wherein said
5 neurotransmitter-secreting cell comprises a neuron.
24. The device of claim 14 wherein said neurotransmitter-secreting cell comprises an adrenal medulla chromaffin cell.
10
25. The device of claim 14 wherein said
neurotransmitter-secreting cell comprises a PC12 cell.
26. The therapy device of claim 14 wherein said
15 neurotransmitter-secreting cell has been genetically engineered to produce said neurotransmitter.
27. The device of claim 14 wherein said growth factor comprises nerve growth factor.
20
28. The device of claim 14 wherein said growth factor comprises fibroblast growth factor.
29. The therapy device of claim 14 wherein said
25 source of growth factor comprises an implantable, biocompatible, polymeric insert containing said growth factor.
30. The device of claim 29 wherein said
30 polymeric insert includes pores having a molecular weight exclusion of from about 1 kD to about 1,000 kD.

31. The device of claim 30 wherein said polymeric insert contains pores having a molecular weight exclusion of about 25 kD to about 100 kD.

5 32. The device of claim 29 wherein said polymeric insert comprises a hydrophobic matrix.

33. The device of claim 32 wherein said hydrophobic matrix comprises ethylene-vinyl acetate
10 copolymer.

34. The device of claim 29 wherein said polymeric insert comprises a hydrophilic matrix.

15 35. The device of claim 34 wherein said hydrophilic matrix comprises a hydrogel.

36. The device of claim 29 wherein said polymeric insert further comprises an impermeable
20 outer coating covering a portion of said insert.

37. The device of claim 36 wherein said impermeable outer coating comprises polyurethane.

25 38. The device of claim 36 wherein said impermeable outer coating comprises ethylene-vinyl acetate.

39. The therapy device of claim 14 wherein said
30 source of growth factor comprises at least one growth factor-secreting cell encapsulated within a semipermeable membrane, said membrane allowing the diffusion therethrough of said growth factor.

40. The therapy device of claim 39 wherein said semipermeable membrane within which said growth factor-secreting cell is encapsulated is impermeable to viruses, antibodies, complement, and proteases.

41. The device of claim 39 wherein said semipermeable membrane includes pores having a molecular weight exclusion of from about 50 kD to about 100 kD.




42. The device of claim 39 wherein said semipermeable membrane comprises an acrylic copolymer.



43. The device of claim 39 wherein said growth factor-secreting cell comprises an allograft.


44. The device of claim 39 wherein said growth factor-secreting cell comprises a xenograft.

45. The device of claim 39 wherein said growth factor-secreting cell comprises a murine submaxillary gland cell.

46. The therapy device of claim 39 wherein said growth factor-secreting cell has been genetically engineered to produce said growth factor.

**FIG. 1A****FIG. 1B****FIG. 1C**

**FIG. 2****FIG. 3**

**FIG. 4**


**FIG. 5**



FIG. 6B




FIG. 6A

SUBSTITUTE SHEET